



PVC-U SCHEDULE 40 & 80 PIPES

a **LESSO** company

★ ★ ★

LEAD-FREE PIPE SYSTEMS

Suitable for Water, Chemical Processing, Waste
water treatment and other industrial applications

LESSO



Schedule 40 & 80 Pipes

Standards & Quality

- Sch. 40 & 80 pipes is manufactured to comply with NSF Standard 61, CSA B 137.3 and ASTM D1785, consistently meeting the Quality Assurance test requirements of the standard with regards to burst pressure, flattening and extrusion quality.



Applications

- Sch. 40 & 80 pipes is resistant to most acids, alkalis, salts, fats, oxidants and halogens. However, those pipe should not be used with ester, ketones, ethers and aromatic or chlorinated hydrocarbons.
- Typical applications include:
 - chemical processing
 - agricultural
 - potable water
 - treated and untreated effluent
 - cooling water
 - irrigation

Temperature Consideration

- Being a thermoplastic material, Sch. 40 & 80 pipes will display variations in its physical properties as the temperature changes. As the temperature falls, the pipe's stiffness and tensile strength increase, thereby increasing the pipe's pressure capacity. Conversely, as the operating temperature rises, the pipe decreases in stiffness and tensile strength; consequently, the pressure capacity of the pipe will be reduced. With the drop in temperature, the pipes decreases in impact strength and becomes less ductile. As the temperature rises, the impact strength and flexibility of the pipe increase.

Thermal Linear Expansion

Sch. 40 & 80 pipes expands and contracts with change in temperature. The coefficient of thermal expansion is 7×10^{-5} mm/mm/°C. This is equivalent to 7mm change in length for every 10 meters for every 10°C change in temperature.

Pressure De-rating Factor

The pressure ratings given are for operating temperature of water at 73°F (23°C). For operating temperature above 73°F (23°C), the working pressure has to be de-rated by multiplying the working pressure of the selected pipe at 73°F (23°C), by the appropriate de-rating factor to determine the maximum permissible working pressure of the pipes at the elevated temperature chosen. Nevertheless, the pipes should not be used at temperature in excess of 140°F (60°C).

OPERATING F°	TEMP C°	DE-RATING FACTOR
73	23	1.00
80	26	0.88
90	32	0.76
100	38	0.64
110	43	0.54
120	49	0.42
130	54	0.32
140	60	0.20

Schedule 40 Pipes (Plain Ended)

Pipes Dimensions & Working Pressures

PRODUCT CODE	NOMINAL DIAMETER		PIPE LENGTH L (M)	OUTSIDE DIAMETER		WALL THICKNESS		MAX WORKING PRESS	
	(in)	(mm)		(in)	(mm)	(in)	(mm)	(psi)	(MPa)
8010013371	½	15	5.8	0.836 - 0.844	21.2 - 21.4	0.110 - 0.130	2.8 - 3.3	600	4.14
Upon request	¾	20	5.8	1.046 - 1.054	26.6 - 26.8	0.114 - 0.134	2.9 - 3.4	480	3.31
8010013372	1	25	5.8	1.310 - 1.320	33.3 - 33.5	0.134 - 0.154	3.4 - 3.9	450	3.10
Upon request	1¼	32	5.8	1.655 - 1.665	42.0 - 42.3	0.142 - 0.161	3.6 - 4.1	370	2.55
8010013373	1½	40	5.8	1.894 - 1.906	48.1 - 48.4	0.146 - 0.165	3.7 - 4.2	330	2.28
8010013374	2	50	5.8	2.369 - 2.381	60.2 - 60.5	0.154 - 0.173	3.9 - 4.4	280	1.93
Upon request	2½	65	5.8	2.868 - 2.882	72.8 - 73.2	0.205 - 0.228	5.2 - 5.8	300	2.07
8010013375	3	80	5.8	3.492 - 3.508	88.7 - 89.1	0.217 - 0.244	5.5 - 6.2	260	1.79
8010013376	4	100	5.8	4.491 - 4.509	114.1 - 114.5	0.236 - 0.264	6.0 - 6.7	220	1.52
Upon request	6	155	5.8	6.614 - 6.636	168.0 - 168.6	0.280 - 0.315	7.1 - 8.0	180	1.24
Upon request	8	200	5.8	8.610 - 8.640	218.7 - 219.5	0.323 - 0.362	8.2 - 9.2	160	1.10
Upon request	10	250	5.8	10.735 - 10.765	272.7 - 273.4	0.366 - 0.409	9.3 - 10.4	0.97	1.40
Upon request	12	300	5.8	12.735 - 12.765	323.5 - 324.2	0.406 - 0.457	10.3 - 11.6	130	0.90

Schedule 80 Pipes (Plain Ended)

Pipes Dimensions & Working Pressures

PRODUCT CODE	NOMINAL DIAMETER		PIPE LENGTH L (M)	OUTSIDE DIAMETER		WALL THICKNESS		MAX WORKING PRESS	
	(in)	(mm)		(in)	(mm)	(in)	(mm)	(psi)	(MPa)
8010013106	½	15	5.8	0.836 - 0.844	21.2 - 21.4	0.147 - 0.167	3.7 - 4.2	850	5.86
8010013113	¾	20	5.8	1.046 - 1.054	26.6 - 26.8	0.154 - 0.17	3.9 - 4.4	690	4.76
8010013085	1	25	5.8	1.310 - 1.320	33.3 - 33.5	0.179 - 0.200	4.6 - 5.1	630	4.34
8010013122	1¼	32	5.8	1.655 - 1.665	42.0 - 42.3	0.191 - 0.214	4.9 - 5.4	520	3.59
8010013121	1½	40	5.8	1.894 - 1.906	48.1 - 48.4	0.200 - 0.224	5.1 - 5.7	470	3.24
8010013089	2	50	5.8	2.369 - 2.381	60.2 - 60.5	0.218 - 0.244	5.5 - 6.2	400	2.76
8010013128	2½	65	5.8	2.868 - 2.882	72.8 - 73.2	0.276 - 0.309	7.0 - 7.8	420	2.90
8010013092	3	80	5.8	3.492 - 3.508	88.7 - 89.1	0.300 - 0.336	7.6 - 8.5	370	2.55
8010013093	4	100	5.8	4.491 - 4.509	114.1 - 114.5	0.337 - 0.377	8.6 - 9.6	320	2.21
8010013096	6	155	5.8	6.614 - 6.636	168.0 - 168.6	0.432 - 0.484	11.0 - 12.3	280	1.93
8010013097	8	200	5.8	8.610 - 8.640	218.7 - 219.5	0.500 - 0.560	12.7 - 14.2	250	1.72
8010013098	10	250	5.8	10.735 - 10.765	272.7 - 273.4	0.593 - 0.664	15.1 - 16.9	230	1.59
8010013100	12	300	5.8	12.735 - 12.765	323.5 - 324.2	0.687 - 0.769	17.5 - 19.5	230	1.59

SCH. 40 & 80 PIPES BENEFITS

Chemical resistance:

The pipes have excellent chemical resistance which allows the transportation of many acids, alkalis and chemical concentrates without fear of corrosion and environmental pollution.

Abrasion resistance:

The pipes offer good resistance to abrasion and erosion from aggressive slurries, which can rapidly damage steel or other traditional pipe materials.

Smooth bore:

The exceptionally smooth bore results in low friction head losses and also inhibits the formation of scale, with consequent savings in pump energy consumption and reduced pressure drops.

Light weight:

At 5 times lighter than steel pipe, Sch. 40 and 80 pipes are much easier to handle, especially during installation at site.

Easy to join:

Solvent welding gives fast and trouble free installation and allows simple modifications to existing systems.



Disclaimer

This brochure has been compiled by **Lesso Malaysia Industries Sdn Bhd** ("the company") to promote better understanding of the technical aspects of the Company's products to assist users in obtaining from them the best possible performance. The brochure is supplied subject to acknowledgment of the following conditions:

i) The brochure is protected by Copyright and may not be copied or reproduced in any form or by any means in whole or in part without prior consent in writing by the Company. ii) Product specifications, usage data and advisory information may change from time to time with advances in research and field experience. The Company reserves the right to make such changes at any time without notice. iii) Correct usage of the Company's products involve engineering judgements which cannot be properly made without full knowledge of all the conditions pertaining to each specific installation. The Company expressly disclaims all and any liability to any person done by any such person in reliance whether whole or partial upon the whole or any part of the contents of this brochure. iv) No offer to trade, nor any conditions of trading, are expressed or implied by the issue or content of this brochure. v) Nothing herein shall override the Company's conditions of Sale, which may be obtained from the Registered Office or any Sales Office of the Company. vi) This brochure is and shall remain the property of the Company, and shall be surrendered on demand to the Company.

LESSO



TRUSTED PIPEWORK FOR LIFE

LESSO MALAYSIA INDUSTRIES SDN BHD

(1380314-K)

Lot 10072 Persiaran Mahagoni Utama 2, Seksyen 4, Bandar Utama Batang
Kali 44300 Batang Kali Selangor Darul Ehsan, Malaysia.

Tel: 603 - 6063 6888 (General) / 603 - 6057 0680. (Sales)

Fax: +603 6057 0680

Email: sales@paling.com.my

Website: www.paling.com.my

Distributed by:

KEKALBOLEH SDN BHD

(199901021248/496148-K)

Lot No. 7, Lorong Perindustrian Kolombong Jaya,

Pusat Perindustrian Kolombong Jaya,

Mile 5.5, Jalan Kolombong,

88450 Kota Kinabalu, Sabah.

Tel/WhatsApp: 088-385555 / 013-8867570

Website: kekalboleh.com